

VESSELS INSIDE AND OUTSIDE

EMAC'07

9TH EUROPEAN MEETING ON ANCIENT CERAMICS

OCTOBER 24-27, 2007

BUDAPEST, HUNGARY

PROGRAM AND ABSTRACTS

Organising Institutions

Hungarian National Museum

with the help of

Archaeocomp Association

Institute of Nuclear Techniques Budapest University of Technology and
Economics

Eötvös Loránd University of Sciences, Department of Archaeometry and
Archaeological Method

Eötvös Loránd University of Sciences, Institute of Geography and Geology
Field Service for Cultural Heritage

Hungarian Archaeological and Art History Society, Archaeometry Workshop
Hungarian Geological Society

Institute for Geochemical Research, HAS

Vienna Institute of Archaeological Science, University of Vienna

Zala County Museum Directorate

P-56**BRONZE AGE POTTERY FROM TRANSYLVANIA
(ROMANIA): A MINERALOGICAL STUDY**Carmen Precup¹ -- Corina Ionescu¹ -- Volker Hoeck² -- Lucretia Ghergari¹ --
Viorica Simon¹¹*Babes-Bolyai University, 1 Kogalniceanu Str., RO-400084 Cluj-Napoca, Romania*²*Salzburg University, 34 Hellbrunner Str., A-5020 Salzburg, Austria*

Middle Bronze Age ceramic potshards found in NW Transylvania (Romania) were studied by plain-polarized light microscopy, XRD, SEM, DTA-TGA and electron microprobe. Microscopically the ceramic body consists of a clayish matrix, in which nonplastic inclusions and voids occur. Various fabrics of matrix can be seen, as function of firing temperature: microcrystalline, microcrystalline-amorphous, amorphous-microcrystalline and amorphous. The inclusions are represented by various crystalloclasts (quartz, plagioclase feldspar, muscovite, calcite, and heavy minerals), lithoclasts (quartzite, micaschist, gneiss, andesite, rhyolite, granite, granodiorite, sandstone, clay) and grog. Granulometrically the samples are either semifine or coarse. The major and trace element analyses show a homogeneous chemical composition: 66-69% SiO₂, 14-15% Al₂O₃, 5-6% Fe₂O₃, ~1.4% MgO, ~2% CaO, ~1% Na₂O, ~2% K₂O, <1% TiO₂, <0.4% P₂O₅. Relatively high amount of Au (4.5-5.2 ppb), Th (7.8–11.1 ppm) and U (1.7-3.1 ppm) as well as REE, may be explained by the adsorption capacity of the raw clays. The source of these elements could have been the metamorphic rocks of the Meses Mts. and the Neogene volcanics of the Eastern Carpathians, respectively. The high value of LOI, ranging from 2.6 to 6.6%, is due to burial alteration.

BSEI shows the presence of new phases, such as melt and reaction rims, as well as newly-formed feldspars. Based on optical microscopy, the modification of the XRD lines of clay minerals, SEM and thermal analyses, a large range of firing temperatures between 750 and 950°C was inferred. Most likely reddish Pleistocene clays occurring west of the site were mixed with alluvial sands from the nearby-located river to obtain the ceramics.